

DALLAS LABORATORIES, INC.

Consultants and Technologists
Chemical and Petroleum Chemists

MEMBERS
AMERICAN CHEMICAL SOCIETY
ASTM INTERNATIONAL
AMERICAN SOCIETY OF MATERIALS

P.O. BOX 152837, DALLAS, TEXAS 75315
1323 WALL ST, DALLAS, TEXAS 75215
PHONE 214/565-0593
FAX 214/565-1094

MEMBERS
AMERICAN NATIONAL STANDARDS INSTITUTE
AMERICAN SOCIETY FOR QUALITY CONTROL
FEDERATION OF SOCIETIES FOR COATINGS TECHNOLOGY

Submitted by: Advanced Heat Exchange
2995 LBJ Frwy., Suite 224
Dallas, TX 75234

Date: September 18, 2009

Attn: Chuck Armstrong

Report No: 41694-F

REPORT

Lab Sample No.

41694 Cement Board (1/2")


PROCEDURE

Sample was tested for compressive yield strength per ASTM D1037.

RESULTS

<u>Test</u>	<u>Sample</u>
Compressive Yield Strength, psi (ASTM D1037)	5210
	4520
	4470
	5085
	<u>4560</u>
	Mean: 4770
Standard Deviation:	350

DALLAS LABORATORIES, INC.


Kevan W. Jones, Vice President

Analyst: TL, KJ
KWJ: JS