

DALLAS LABORATORIES, INC.

Consultants and Technologists
Chemical and Petroleum Chemists

MEMBERS
AMERICAN CHEMICAL SOCIETY
ASTM INTERNATIONAL
AMERICAN SOCIETY OF MATERIALS

P.O. BOX 152837, DALLAS, TEXAS 75315
1323 WALL ST, DALLAS, TEXAS 75215
PHONE 214/565-0593
FAX 214/565-1094

MEMBERS
AMERICAN NATIONAL STANDARDS INSTITUTE
AMERICAN SOCIETY FOR QUALITY CONTROL
FEDERATION OF SOCIETIES FOR COATINGS TECHNOLOGY

Submitted by: Omniroc, Inc.
Advanced Heat Exchange, Inc.
2995 LBJ Frwy., Suite 224
Dallas, TX 75234

Date: September 24, 2009

Attn: Chuck Armstrong

Report No: 41694-N

REPORT

Lab Sample No.

41694 Cement Board (1/2")

PROCEDURE

Sample was tested for combustible properties and behavior per ASTM E136. Sample is tested using four (4) specimens for ten (10) minutes under air at 750°C.


RESULTS

<u>Property/Behavior</u>	<u>Spec. #1</u>	<u>Spec. #2</u>	<u>Spec. #3</u>	<u>Spec. #4</u>	<u>Requirements</u>
Weight Loss, %	9.2	8.8	9.0	9.1	≤50.0
Exotherm (Temperature Rise)	2.0	2.5	2.0	3.0	≤30.0
Flaming After Initial 30 Seconds	None	None	None	None	None
Pass/Fail	Pass	Pass	Pass	Pass	

DISCUSSION

Sample passes the ten (10) minute exposure test at 750°C per ASTM E136.

DALLAS LABORATORIES, INC.


Kevan W. Jones, Vice President

Analyst: TL, KJ
KWJ: JS