

# DALLAS LABORATORIES, INC.

Consultants and Technologists  
Chemical and Petroleum Chemists

MEMBERS  
AMERICAN CHEMICAL SOCIETY  
ASTM INTERNATIONAL  
AMERICAN SOCIETY OF MATERIALS

P.O. BOX 152837, DALLAS, TEXAS 75315  
1323 WALL ST, DALLAS, TEXAS 75215  
PHONE 214/565-0593  
FAX 214/565-1094

MEMBERS  
AMERICAN NATIONAL STANDARDS INSTITUTE  
AMERICAN SOCIETY FOR QUALITY CONTROL  
FEDERATION OF SOCIETIES FOR COATINGS TECHNOLOGY

Submitted by: Advanced Heat Exchange  
2995 LBJ Frwy., Suite 224  
Dallas, TX 75234

Date: September 18, 2009

Attn: Chuck Armstrong

Report No: 41694-B

## REPORT

### Lab Sample No.

41694      Cement Board (1/2")

## PROCEDURE

Sample was cut and tested for unnotched Izod impact strength per ASTM D256 (Method B).

## RESULTS

### Test

### Sample

IZOD Impact Resistance, ft/lbs/in (Break)  
(ASTM D256, Method B)


0.62 (CB)  
0.51 (CB)  
0.55 (CB)  
0.58 (CB)  
0.68 (CB)

Mean: 0.59

Standard Deviation: 0.07

CB – Complete Break

DALLAS LABORATORIES, INC.

  
Kevan W. Jones, Vice President

Analyst: TL, KJ  
KWJ: JS