

DALLAS LABORATORIES, INC.

Consultants and Technologists
Chemical and Petroleum Chemists

MEMBERS
AMERICAN CHEMICAL SOCIETY
ASTM INTERNATIONAL
AMERICAN SOCIETY OF MATERIALS

P.O. BOX 152837, DALLAS, TEXAS 75315
1323 WALL ST, DALLAS, TEXAS 75215
PHONE 214/565-0593
FAX 214/565-1094

MEMBERS
AMERICAN NATIONAL STANDARDS INSTITUTE
AMERICAN SOCIETY FOR QUALITY CONTROL
FEDERATION OF SOCIETIES FOR COATINGS TECHNOLOGY

Submitted by: Advanced Heat Exchange
2995 LBJ Frwy., Suite 224
Dallas, TX 75234

Date: September 24, 2009

Attn: Chuck Armstrong

Report No: 41694-G

REPORT

Lab Sample No.

41694 Cement Board (1/2")


PROCEDURE

Sample was submerged horizontally for 24 hours in distilled water and evaluated for saturated thickness swelling per ASTM D1037.

RESULTS

<u>Test</u>	<u>Sample</u>
Saturated Thickness Swelling, % (ASTM D1037)	0.73

DALLAS LABORATORIES, INC.


Kevan W. Jones, Vice President

Analyst: TL, KJ
KWJ: JS